

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 September 2002 (06.09.2002)

PCT

(10) International Publication Number
WO 02/068167 A1

- (51) International Patent Classification⁷: **B29C 33/52**, B29L 22/00
- (21) International Application Number: PCT/EP01/11214
- (22) International Filing Date:
27 September 2001 (27.09.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
01810190.7 23 February 2001 (23.02.2001) EP
- (71) Applicant (*for all designated States except US*): **VAN-TICO AG** [CH/CH]; Klybeckstrasse 200, CH-4057 Basel (CH).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): **HOCHWALD, Peter** [DE/DE]; Günnenbacher Strasse 5a, 79664 Wehr (DE).
- (74) Agents: **HEDLEY, N.J.M.** et al.; Killburn & Strode, 20 Red Lion Street, London WC1R 4PJ (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 02/068167 A1

(54) Title: METHOD FOR PRODUCING MODELS

(57) Abstract: The invention relates to a method for producing models or pre-forms, comprising the following method steps: (a) producing a shaped core from a water-soluble block material, (b) coating the shaped core with a curable polymer, (c) curing the curable polymer at from 25 to 250 °C, and (d) removing the core material by treating the coated core with water.

Method for producing models

The present invention relates to a method for producing models or pre-forms by the "lost core" method.

A conventional method for producing plastics models of complex mouldings having cavities requires a negative prototype to be modelled from a block material, which is then coated with a curable polymer. After the polymer has been fully cured, the inner block material is removed ("lost core"). Depending upon the nature of the block material used and of the polymer cured, removal is carried out by melting or by dissolving in a suitable solvent. Wax, polystyrene or other meltable plastics mixtures have hitherto been used as block materials. In SAMPE Journal, Vol. 36, No. 4, 46-48 (2000), a polyisocyanurate foam is proposed for producing motor housings. The polyisocyanurate foam is easy to process, is temperature-resistant up to 180°C and is compatible with various synthetic resins, for example epoxides, bismaleimides and phenolic resins. Removal of the block material is carried out using high-pressure washing systems.

The problem of the present invention was to simplify the known methods and to reduce the amount of waste.

The present invention relates to a method for producing models or pre-forms, comprising the following method steps:

- (a) producing a shaped core from a water-soluble block material,
- (b) coating the shaped core with a curable polymer,
- (c) curing the curable polymer at from 25 to 250°C, and
- (d) removing the core material by treating the coated core with water.

The environmental burden of the method according to the invention is minimal because no organic solvents are used and the water-soluble block material can be recovered and recycled.

Production of the shaped core in method step (a) is carried out by known shaping methods, for example milling, grinding, casting or compression moulding.

The water-soluble block material should be capable of being shaped easily and have some degree of temperature-resistance.

Preferred block materials are water-soluble polymers, for example polyacrylic acid, polymethacrylic acid and, especially, polyvinyl alcohol.

It is advantageous to apply a parting agent to the shaped core before it is coated with the curable polymer. Suitable parting agents are, for example, fatty acids, fatty acid esters, fatty acid salts, e.g. zinc stearate or calcium stearate, and silicones. Instead of coating with a parting agent, it is also possible to wrap the shaped core with a Teflon tape.

The polymer used in method step (b) can be a thermally curable or radiation-curable polymer. Preference is given to the use of a thermally curable (thermosetting) polymer.

Suitable curable polymers are, for example, epoxy resins, phenolic resins, unsaturated polyesters, bismaleimides, polyimides and polyurethanes.

Special preference is given to epoxy resins.

Examples of suitable epoxy resins are diglycidyl ethers of bisphenols, e.g. diglycidyl ether of bisphenol A and diglycidyl ether of bisphenol F, epoxy phenol novolaks, epoxy cresol novolaks, cycloaliphatic epoxy resins, e.g. 3,4-epoxycyclohexylmethyl 3',4'-epoxycyclohexanecarboxylate, diglycidyl tetrahydrophthalate, diglycidyl 4-methyltetrahydrophthalate, diglycidyl hexahydrophthalate and diglycidyl 4-methylhexahydrophthalate, and N-glycidyl compounds such as triglycidyl isocyanurate.

The curable polymer can comprise customary auxiliaries and additives, for example antioxidants, light stabilisers, flame retardants, fillers, plasticisers, dyes, pigments, thixotropic agents, toughness improvers, antifoams, antistatics, lubricants and mould-release aids.

The curable polymer preferably comprises fillers in powder form, for example quartz powder or aluminium oxide.

The shaped core is generally coated with the curable polymer by conventional methods, for example application by injection, spraying, casting, the filament winding technique or the hand lay-up method.

The curable polymer is then fully cured at room temperature or at elevated temperature, the curing temperature and duration of curing depending both on the nature of the curable polymer and on the hardener and/or accelerator chosen. Suitable hardeners and curing accelerators will be well known to the person skilled in the art.

Preference is given to the selection of a resin/hardener system that fully cures in the temperature range from 50 to 150°C, especially from 80 to 140°C.

The curing process can be carried out at normal pressure in an oven or under pressure in an autoclave.

After curing of the polymer, the shaped core can be removed very simply by dissolving in water. Most simply, that is carried out by immersing the coated core in a water bath.

In the case of very soluble block materials, for example polyvinyl alcohol, the use of cold water is sufficient; less readily soluble materials can be removed using warm or hot water or by the use of pressure.

Preference is given to carrying out method step (d) at room temperature (15 - 25°C) and under normal pressure (900 - 1100 hPa).

After method step (d) has been carried out, the filler optionally contained in the block material can be recovered and put to the same or some other use.

The water-soluble block material can also be completely recovered by evaporating off the water.

Example 1

A mixture of 10 parts by weight of polyvinyl alcohol and 100 parts by weight of $\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$ is shaped into a negative model of a hollow article. An epoxy resin/hardener mixture (diglycidyl ether of bisphenol A) is then applied to the negative model. Pretreatment with a

parting agent is not necessary. The time for full cure depends on the layer thickness of the block; for each centimetre of layer thickness, curing for 1 hour at at least 60°C is necessary. After full cure, the block material is dissolved out from the inside of the hollow article in water.

Example 2

A mixture of 20 parts by weight of polyvinyl alcohol and 100 parts by weight of ALU DIN 100 (aluminium powder, 100 μm) is shaped into a negative model of a hollow article. An epoxy resin/hardener mixture (diglycidyl ether of bisphenol A) is then applied to the negative model. Pretreatment with a parting agent is not necessary. The time for full cure depends on the layer thickness of the block; for each centimetre of layer thickness, curing for 1 hour at at least 60°C is necessary. After full cure, the block material is dissolved out from the inside of the hollow article in water.

What is claimed is:

1. A method for producing models or pre-forms, comprising the following method steps:
 - (a) producing a shaped core from a water-soluble block material,
 - (b) coating the shaped core with a curable polymer,
 - (c) curing the curable polymer at from 25 to 250°C, and
 - (d) removing the core material by treating the coated core with water.
2. A method according to claim 1, wherein a water-soluble polymer is used as the block material in method step (a).
3. A method according to claim 2, wherein polyvinyl alcohol is used as the block material in method step (a).
4. A method according to claim 1, wherein the curable polymer in method step (b) is selected from epoxy resins, phenolic resins, unsaturated polyesters, bismaleimides, polyimides and polyurethanes.
5. A method according to claim 1, wherein the curing of the curable polymer in method step (c) is carried out at from 50 to 150°C.
6. A method according to claim 1, wherein method step (d) is carried out at room temperature (15 - 25°C) and under normal pressure (900 -1100 hPa).

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/11214

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C33/52 B29L22/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 195 34 836 A (RIESELMAH F & H KUNSTSTOFF) 27 March 1997 (1997-03-27) the whole document	1-6
X	US 5 184 874 A (OLSON PAUL D ET AL) 9 February 1993 (1993-02-09) column 2, line 57 - line 60 column 4, line 33 - line 66	1-6
X	DATABASE WPI Section Ch, Week 8437, September 1984 (1984-09) Derwent Publications Ltd., London, GB; Class A32, AN 1984-228589 37! XP002173854 & JP 59 136214 A (NIIGATA ENG CO LTD), 4 August 1984 (1984-08-04) abstract; figures	1,2,4-6

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

4 March 2002

Date of mailing of the international search report

11/03/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mathey, X

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/11214

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 19534836	A	27-03-1997	DE 19534836 A1	27-03-1997
US 5184874	A	09-02-1993	WO 9416911 A1	04-08-1994
			AU 693419 B2	02-07-1998
			AU 3656793 A	15-08-1994
			AT 207419 T	15-11-2001
			DE 69331015 D1	29-11-2001
			DK 680414 T3	31-12-2001
			EP 0680414 A1	08-11-1995
			JP 8509182 T	01-10-1996
			NZ 249637 A	27-05-1998
JP 59136214	A	04-08-1984	JP 1005806 B	01-02-1989
			JP 1524967 C	12-10-1989